

Update: November 1, 2022

DHT™-4C

"DHT[™]-4C" is dehydrated Hydrotalcite-like Compound and has the unique anion-exchange property. "DHT[™]-4C" has been developed for use as stabilizer in the resins processing at high temperature such as engineering plastics and rubbers.

"DHT[™]-4C" is more suitable for use in the resins processing at high temperature, because the heat resistance of "DHT[™]-4C" is higher than "DHT-4A[™]-2".

【Typical Data】

	DHT [™] -4C
Molar Ratio of MgO/Al ₂ O ₃	4.25
Loss on heating $(300^{\circ}C \times 1Hr)$ (%)	4.1
Specific Surface Area (BET) (m²/g) 15
Particle Size Distribution	
Average %50 (µm)	0.38

Package	NET weight
Paper bag	15 kg

'DHT' and 'DHT-4A' are registered trademarks of SETOLAS Holdings, Inc. in many countries.

