

## DHT-4A-2

“DHT-4A-2” is dehydrated Hydrotalcite-like Compound and has the unique anion-exchange property. It has been developed for use as stabilizer in the resins processing at high temperature such as engineering plastics and rubbers.

### 【Typical Data】

			DHT-4A-2
Molar Ratio of MgO/Al <sub>2</sub> O <sub>3</sub>			4.29
Loss on Drying(250°C × 1Hr)	(%)		3.3
Specific Surface Area (BET)	(m <sup>2</sup> /g)		13
Particle Size Distribution			
Average	%50	(μg)	0.40
Over	5μm	(vol%)	0.0

Package	NET weight
Paper Bag	20 kg