

## DHT-4A™-2

“DHT-4A™-2” is dehydrated Hydrotalcite-like Compound and has the unique anion-exchange property. It has been developed for use as stabilizer in the resins processing at high temperature such as engineering plastics and rubbers.

### 【Typical Data】

|   |     |                     | DHT-4A™-2 |
|---|-----|---------------------|-----------|
| Molar Ratio of MgO/Al <sub>2</sub> O <sub>3</sub> |     |                     | 4.30      |
| Loss on Drying(250°C × 1Hr)                       |     | (%)                 | 3.5       |
| Specific Surface Area (BET)                       |     | (m <sup>2</sup> /g) | 12        |
| Particle Size Distribution                        |     |                     |           |
| Average   | %50 | (μm)                | 0.37      |
| Over  | 5μm | (vol%)              | 0.0       |

| Package   | NET weight |
|-----------|------------|
| Paper Bag | 20 kg      |

‘DHT’ and ‘DHT-4A’ are registered trademarks of SETOLAS Holdings, Inc. in many countries.